

Product datasheet Kneton-Lab 95



1. Manufacturer information

Trade name:	Kneton-Lab 95
Intended use:	Fabrication of sectional moulds
Manufacturer:	Erkodent Erich Kopp GmbH Siemensstraße 3 72285 Pfalzgrafenweiler Germany Tel.: +49 7445 8501-0

2. Intended use

Condensation-cured, stable laboratory moulding material for fabrication of sectional moulds in case of repairs, for the use with hot- and cold-curing acrylics, for insulation of artificial teeth.

3. Properties

Technical properties:

Properties	Guideline	Value
Form	ISO 4823:2015	mouldable
Colour	-	white
Odour	-	characteristic
Density	ISO 1183	1,69 g/cm ³
Hardness shore A	ISO 868	± 95
Minimum durability	-	36 months

4. General information

Storage instructions:

Keep away from sunlight. Keep dry.
Recommended storage temperature: 5°C – 35°C
Recommended working temperature: 15°C – 25°C

Instructions for cleaning and maintenance:

Do not bring into contact with disinfectants or similar.

The information on this product data sheet corresponds to the best of our knowledge at the time of printing. The information is not guaranteed assurance of product properties and does not constitute a contractual legal understanding. Input errors and mistakes reserved.